



Application

The coating solution selected was Enviroline 2405, a high solids thick film epoxy designed for rapid cure in petrochemical industry applications. The heavy build of this product (16-45 mils) provided additional assurance that a holiday free coating could be achieved despite areas affected by corrosion. Coating was applied to the bottom 40% of 10' x 45' treater.

Our goal was a four day turn around. Ar-Tech professionals were able to SSPC-SP6 commercial blast and SSPC-SP5 white blast using copper slag blast media on first day. The first coat of EC-2405 was then applied on day two with the final coat applied on day three. Day four was final inspection using low voltage elcometer giving our customer a 100% holiday free and cured product. Customer is also given a two year warranty.

